

**AHLSTROM-MUNKSJÖ GRADE 613
TECHNICAL SPECIFICATIONS**

Composition: Cellulose

Appearance: White, Unfinished

PROPERTY	Minimum	Aim	Maximum
Basis Weight (Lbs/1389 square feet)	19	20	21
Basis Weight (gsm)	66.8	70.3	73.8
Rapidity (mls/min)	50	60	70
Wet Burst (inches of water)	10	16	23
MD Wet Tensile (lbs/1 inch)	0	3	5
Air Bubbles (pass(2)/fail(0))	1		2

Values given are typical reel averages for this grade. Individual observations may vary slightly from these values.