

**AHLSTROM-MUNKSJÖ GRADE 909  
TECHNICAL SPECIFICATIONS**

**Composition:** Cellulose

**Appearance:** White, Unfinished

<b>PROPERTY</b>	<b>Minimum</b>	<b>Aim</b>	<b>Maximum</b>
<b>Basis Weight (Lbs/1389 square feet)</b>	<b>19</b>	<b>20</b>	<b>21</b>
<b>Basis Weight (gsm)</b>	<b>66.8</b>	<b>70.3</b>	<b>73.8</b>
<b>Rapidity (mls/min)</b>	<b>50</b>	<b>65</b>	<b>85</b>
<b>Wet Burst (inches of water)</b>	<b>90</b>	<b>120</b>	<b>150</b>
<b>Formation (number(1-10))</b>	<b>6</b>	<b>8</b>	<b>10</b>
<b>CD Wet Tensile (lbs/1 inch)</b>	<b>0</b>	<b>7</b>	<b>15</b>
<b>Air Bubbles (pass(2)/fail(0))</b>	<b>1</b>		<b>2</b>

**Values given are typical reel averages for this grade. Individual observations may vary slightly from these values.**