

**AHLSTROM-MUNKSJÖ GRADE 939
TECHNICAL SPECIFICATIONS**

Composition: Cellulose

Appearance: White, Unfinished

PROPERTY	Minimum	Aim	Maximum
Basis Weight (Lbs/1389 square feet)	38	40	41
Basis Weight (gsm)	133.6	140.6	144.1
Thickness (mils)	24	27.5	31
Thickness (microns)	609.6	698.5	787.4
Frazier (cfm)	30	35	40
Wet Burst (inches of water)	150	200	258
Formation (number(1-10))	6	8	10
MD Wet Tensile (lbs/1 inch)	2	5	10

Values given are typical reel averages for this grade. Individual observations may vary slightly from these values.