

**AHLSTROM-MUNKSJÖ GRADE 950  
TECHNICAL SPECIFICATIONS**

**Composition:** Cellulose

**Appearance:** White, Smooth

<b>PROPERTY</b>	<b>Minimum</b>	<b>Aim</b>	<b>Maximum</b>
<b>Basis Weight (Lbs/1389 square feet)</b>	<b>24</b>	<b>25</b>	<b>26</b>
<b>Basis Weight (gsm)</b>	<b>84.4</b>	<b>87.9</b>	<b>91.4</b>
<b>Thickness (mils)</b>	<b>7.0</b>	<b>7.8</b>	<b>9.0</b>
<b>Thickness (microns)</b>	<b>177.8</b>	<b>196.9</b>	<b>228.6</b>
<b>Rapidity (mls/min)</b>	<b>8</b>	<b>14</b>	<b>20</b>
<b>Wet Burst (inches of water)</b>	<b>90</b>	<b>122</b>	<b>172</b>
<b>MD Wet Tensile (lbs/inch)</b>	<b>1</b>	<b>5</b>	<b>10</b>
<b>Air Bubbles (2-pass, 0-fail)</b>	<b>0</b>	<b>2</b>	<b>2</b>
<b>MD Edge Tare (lbs/inch)</b>	<b>3.0</b>	<b>6.5</b>	<b>10.0</b>
<b>Moisture (%)</b>	<b>0</b>	<b>2.0</b>	<b>5.0</b>
<b>Dirt Count (PPM)</b>	<b>0</b>	<b>0</b>	<b>3</b>

**Values given are typical reel averages for this grade. Individual observations may vary slightly from these values.**